

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**




FIG. 1

FIG. 1
(C)





FIG. 1
(E)






FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 6




FIG. 7




FIG. 8

(a)

(b)

Explosive/ Taggant	No Dopant	CH ₂ Br ₂ , 2%	CH ₂ Cl ₂ , 2.5%	CH ₃ OH, 1%	Isopropanol, 2%
	✓, Negative V _c =-0.23 Rf 950V, Air, 120 C, 1atm long drag, inlet T 150- >190C, Oven T 50->100C, 80C/m->100C/m	✓, Negative V _c =-4.9 Rf 950V, Air, 120 C, 1atm long drag, inlet T 150- >190C, Oven T 50->100C, 80C/m->100C/m	✓, Negative V _c =-6.1 Rf 950V, Air, 120 C, 1atm long drag, inlet T 150- >190C, Oven T 50->100C, 80C/m->100C/m	GC temperature was low, HMX did not move.	Not measured
HMX t=95 sec					
	✓, Negative	Not measured	✓, Negative	✓, Negative	Not measured
	V _c =-0.23 Rf 950V, Air, 120 C, 1atm inlet T 150, Oven T 50, 80C/min split 5:1, f=8 cc/min unless specifically noted, other molecules are under same GC conditions		Two peaks V _c =-1.99, -6.68, Rf 950V, Air, 120 C, 1atm	V _c =-0.82 Rf 950V, Air, 120 C, 1atm	
Tetryl t=116 sec t=160 sec					
	✓, Negative	✓, Negative	✓, Negative	✓, Negative	✓, Negative
	V _c =-0.23 Rf 950V, Air, 120 C, 1atm, mix6x10	V _c =-7.9 Rf 1050V, N ₂ , 120 C, 1atm, 1 uL, 0.1 mg/ml long drag	V _c =-5.51 Rf 950V, Air, 120 C, 1atm, mix6x10	V _c =-1.5 Rf 950V, Air, 120 C, 1atm, mix6x10 GC column flow was low	V _c =-5.51 Rf 1050V, N ₂ , 120 C, 1atm, 1 uL, 0.1 mg/ml
PETN t=104 sec					

FIG. 9 (Part 1)


Explosive/ Taggant	No Dopant	CH ₂ Br ₂ , 2%	CH ₂ Cl ₂ , 2.5%	CH ₃ OH, 1%	Isopropanol, 2%
	✓, Negative ✓, Positive	✓, Negative	✓, Negative ✓, Positive	✓, Negative	✓, Negative
RDX t=37 sec(+) t=72 sec(-)	Vc=-0.3, --negative Vc=-4.92, --positive Rf 950V, Air, 120 C, 1atm, mix6x10 Pos and neg are at different retention time, break down effect	Vc=-9, Rf 1050V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml	Vc=-8.43, --negative Vc=-6.68, --positive Rf 950V, Air, 120 C, 1atm, mix6x10 Pos and neg are at different retention time, break down effect	Vc=-2.58, Rf 950V, Air, 120 C, 1atm, mix6x10 no Pos ion shown, MeOH depressed it.	Vc=-6.68, Rf 1050V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml
	✓, Negative	✓, Negative	✓, Negative	✓, Negative	✓, Negative
NG t=31 sec	Two Peaks Vc=-0.23, -20.7, Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-10, Rf 1050V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml	one peak Vc=-9.6, Rf 950V, Air, 120 C, 1atm, mix6x10	Two peaks Vc=-2.58, -33.7, Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-10, Rf 1050V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml
	✓, Negative	X	✓, Negative	✓, Negative	✓, Negative
TNT t=72 sec	Vc=-0.82, Rf 950V, Air, 120 C, 1atm, mix6x10		Vc=-2.58, Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-0.82, Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-10, Rf 1050V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml
	✓, Negative	X?	✓, Negative	✓, Negative	✓, Negative
EGDN t=10 sec	Vc=-20, Rf 950V, Air, 120 C, 1atm, mix6x10		Vc=-34, Rf 950V, Air, 120 C, 1atm, 2 uL, 0.1 mg/ml peak too close to MeCl ₂ (- 36 V)	Vc=-33.7, Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-30, Rf 850V, N2, 120 C, 1atm, 1 uL, 0.1 mg/ml peak too close to Isopropanol (-32 V)
	✓, Negative	X	X	✓, Negative	✓, Negative
DNT t=48 sec	Vc=-1.7 Rf 950V, Air, 120 C, 1atm, mix6x10	no peaks	no peaks	Vc=-2 Rf 950V, Air, 120 C, 1atm, mix6x10	Vc=-16.7 Rf 950V, N2, 120 C, 1atm, weak signal decreased by 20 times

FIG. 9 (Part 2)

Explosive/ Taggant	No Dopant	CH ₂ Br ₂ , 2%	CH ₂ Cl ₂ , 2.5%	CH ₃ OH, 1%	Isopropanol, 2%
	✓, Positive	Not measured	✓, Positive	X	Not measured
O-MNT Taggant t=16 sec	V _c =-17.8, Rf 950V, Air, 120 C, 1atm, too close to RIP		V _c =-14.3, Rf 950V, Air, 120 C, 1atm, too close to RIP		
	✓, Positive	Not measured	✓, Positive	X	Not measured
p-MNT Taggant 19 sec	V _c =-16.7, Rf 950V, Air, 120 C, 1atm, too close to RIP		V _c =-14.9, Rf 950V, Air, 120 C, 1atm, too close to RIP		
	✓, Positive	Not measured	✓, Positive	X	Not measured
DMNB t=17 sec	V _c =-7.9, Rf 950V, Air, 120 C, 1atm		V _c =-9, Rf 950V, Air, 120 C, 1atm		
	✓, Positive	Not measured	✓, Positive	✓, Positive	X
TATP t=13 sec	V _c =-8.43, Rf 950V, Air, 120 C, 1atm		V _c =-10.8, Rf 950V, Air, 120 C, 1atm	V _c =-5, Rf 950V, Air, 120 C, 1atm	
	✓, Positive	Not measured	✓, Positive	✓, Positive	X
HMTD t=49 sec	V _c =1.5, Rf 950V, Air, 120 C, 0.6atm old sample		V _c =-1.4, Rf 950V, Air, 120 C, 1atm new sample	V _c =-0.82, Rf 950V, Air, 120 C, 1atm old sample	
	✓, Negative ✓, Positive	Not measured	✓, Negative ✓, Positive	Not measured	✓, Negative
AN t(+)=3 sec t(-)=6 sec	V _c =-19.6, --negative V _c =-19.6, --positive Rf 950V, air, 120 C, 1atm Pos and neg are at different retention time, break down to NH ₃ (+) and HNO ₃ (-)		V _c =-41.83, --negative V _c =-24.3, --positive Rf 950V, air, 120 C, 1atm Pos and neg are at different retention time, break down to NH ₃ (+) and HNO ₃ (-)		V _c =-3.75, Rf 950V, Air, 120 C, 1atm, mix6x10 no Pos ion shown, Isopropanol depressed it.

FIG. 9 (Part 3)

Electron Affinity



Proton Affinity



FIG. 10




FIG. 11a




FIG. 11b




FIG. 12a




FIG. 12b




FIG. 13a




FIG. 13b




FIG. 14a




FIG. 14b